


COLLECTION | HERRINGBONE
COLOR | FOGGY DAWN

Wood species | American Walnut
Grade | 1 Natur
Constructions | 3-layer T&G Engineered Flooring
Size | 19,05 x 127 x 635 mm (¾" x 5" x 25")
Finish | Silk mat finish

CONSTRUCTION : 3-LAYER T&G ENGINEERED FLOORING

DIMENSIONS :	
Thickness	19,05 mm (¾")
Width	127 mm (5")
Length	635 mm (25")
Cut angle	90°
Microbevel	0,5 mm
Joint type	tongue and groove (T&G)



PACKAGING :	BOX	PALLET
	Content:	1,29 m ²
Weight	17 kg	903 kg
H x W x L	153 x 269 x 663 mm	1080 x 832 x 2050 mm
Content:	13,88 sq.ft.	749,52 sq.ft.
Weight	37,6 lb	1998 lb
H x W x L	6" x 11" x 27"	42" x 32" x 80"

DEVIATIONS :		
Deviation on Thickness	± 0,2 mm	EN 13489 ГОСТ 862.3
Deviation on Width	± 0,2 mm	
Height Difference	≤ 0,2 % of width	
Cup	≤ 0,2 % of plank width	EN 13489
Spring	≤ 0,1 % of length	
Bow	≤ 0,5 % of length	

CHARACTERISTICS :		
Fire resistance	Dfl-s1	EN 14342
Formaldehyde emission class	E1	
Pentachlorophenol content	None	
Thermal resistance	0,118 m ² ·K/W	
Thermal conductivity	0,161 W/(m·K)	
Structural warranty	Lifetime	

INSTALLATION :	STORAGE AND USAGE :
<p>Glue down over concrete, plywood or wooden subfloor or nail down over wooden subfloor. Applicable above, on and below ground level.</p>	<p>— Air humidity 40% – 65% — Temperature +18 °C – +22 °C</p>

FINISH : SILK MAT FINISH

DESCRIPTION :	
Type of coating	UV-cured modified polyurethane-acrylate
Surface (finish) type	Semi-closed pores, wire brushed
Sheen	Matte 2-7 GU/60°
Finish warranty	-

CLASSIFICATION SURFACE CHARACTERISTICS :		
Wear resistance	Not rated	EN 438-2
Scratch resistance	Not rated	EN 438
Slip resistance	50 (SRV dry)	EN 15676
Resistance to chemical agents	Class 5 (Except blue ink)	EN 13442
Repairability	Medium	

MAINTENANCE AND CARE CONDITIONS :

Maintenance of hardwood floors with Silk finish assumes regular (daily if necessary) cleaning from dust and grit using a vacuum, followed by a thorough cleaning with Coswick Hardwood Floor Cleaner or other similar product. Floor surface areas that receive the most traffic and get worn down quicker, such as areas by the front door, hallways, kitchens etc., should be periodically renewed with special Coswick Restorative Oil. This product restores the protective surface film. Frequency of use depends on type of interior and intensity of foot traffic. For residential interiors, restorative cleaning should be done once in 3-5 years; for public and commercial interiors with intense foot traffic, it is recommended to use the product 2-4 times a year.

GRADE : 1 NATUR

DESCRIPTION :		DESCRIPTION :	
Sound sapwood	Permitted non-contrasting up to 25% of the plank area	Bark pocket	Permitted up to 50 mm in length, up to 5 mm in width, filled
Colour variation	Allowed	Pith	Permitted
Knot	Permitted up to 35 mm, filled	Slope of grain	Permitted
Cracks	Not permitted	Medullary ray	Permitted